

(12) **UK Patent Application** (19) **GB** (11) **2 389 708** (13) **A**

(43) Date of A Publication 17.12.2003

(21) Application No: 0308656.8

(22) Date of Filing: 15.04.2003

(30) Priority Data:

(31) 60372673	(32) 15.04.2002	(33) US
(31) 60435218	(32) 19.12.2002	
(31) 10409036	(32) 08.04.2003	

(71) Applicant(s):

**AVX Corporation**  
**(Incorporated in USA - Delaware)**  
**PO Box 867, 2200 AVX Drive,**  
**Myrtle Beach, South Carolina 29578-0867,**  
**United States of America**

(72) Inventor(s):

**Robert H Helstand II**  
**John L Galvagni**  
**Andrew Ritter**  
**Jason MacNeal**  
**Sriram Dattaguru**

(continued on next page)

(51) INT CL<sup>7</sup>:  
H01G 4/232(52) UK CL (Edition V):  
H1M MCE MDX2 M1P11 M1P6 M1P7(56) Documents Cited:  
JP 060168845 A JP 2002164257 A  
US 5880925 A(58) Field of Search:  
UK CL (Edition V) H1M  
INT CL<sup>7</sup> H01G, H05K  
Other: Online: EPODOC, JAPIO, WPI(54) Abstract Title: **Plated terminations for an electronic component**

(57) Monolithic components are provided with plated terminations whereby the need for typical thick-film termination stripes is eliminated or greatly simplified. The plated terminations 130 are guided and anchored by exposed varying width internal electrode tabs 114, 116 and additional anchor tab portions 118, 120. Such anchor tabs may be positioned internally or externally relative to a chip structure to nucleate additional metallized plating material 130. The combination of electrode tabs and anchor tabs may be exposed in respective arrangements to form generally discoidal portions of plated material. Such plated material may ultimately form generally round portions of ball limiting metallurgy (BLM) to which solder balls may be reflowed. The disclosed technology may be utilized with a plurality of monolithic multi layer components 100, including interdigitated capacitors, multilayer capacitor arrays, and integrated passive components.




FIG. 5




FIG. 6

GB 2 389 708 A

**GB 2389708 A continuation**

**(74) Agent and/or Address for Service:**

**Barker Brettell**

**138 Hagley Road, Edgbaston,**

**BIRMINGHAM, B16 9PW, United Kingdom**




Fig. 2 (Prior Art)




Fig. 1 (Prior Art)




FIG. 3




FIG. 4

216





FIG. 6

FIG. 5




FIG. 7




FIG. 8




Fig. 10




Fig. 9




Fig. 11

416




FIG. 13




FIG. 12




FIG. 14

516




FIG. 15




FIG. 16




FIG. 17






FIG. 18





5

**COMPONENT FORMATION VIA PLATING TECHNOLOGY**

10

15

**BACKGROUND OF THE INVENTION**

The present subject matter generally concerns improved component formation for multilayer electronic components. More particularly, the present subject matter relates to the utilization of plating technology in termination and inductive component formation as well as for interconnection techniques for devices such as multilayer capacitors or integrated passive components. The subject technology utilizes selective arrangements of exposed electrode tabs to facilitate the formation of plated electrical connections.

Many modern electronic components are packaged as monolithic devices, and may comprise a single component or multiple components within a single chip package. One specific example of such a monolithic device is a multilayer capacitor or capacitor array, and of particular interest with respect to the disclosed technology are

multilayer capacitors with interdigitated internal electrode layers and corresponding electrode tabs.

Examples of multilayer capacitors that include features of interdigitated capacitor (IDC) technology can be found in  
5 U.S. Patent Nos. 4,831,494 (Arnold et al), 5,880,925 (DuPré et al.) and 6,243,253 B1 (DuPré et al.). Other monolithic electronic components correspond to devices that integrate multiple passive components into a single chip structure. Such an integrated passive component may provide a selected  
10 combination of resistors, capacitors, inductors and/or other passive components that are formed in a multilayered configuration and packaged as a monolithic electronic device.

Selective terminations are often required to form  
15 electrical connections for various monolithic electronic components. Multiple terminations are needed to provide electrical connections to the different internal electronic components of an integrated monolithic device. Multiple terminations are also often used in conjunction with IDC's  
20 and other multilayer arrays in order to reduce undesirable inductance levels. One exemplary way that multiple terminations have been formed in multilayer components is by drilling vias through selected areas of a chip structure and filling the vias with conductive material such that an  
25 electrical connection is formed among selected electrode portions of the device.

Another way of forming external terminations for the subject devices is to apply a thick film stripe of silver or copper in a glass matrix to exposed portions of internal  
30 electrode layers, curing or firing that material, and subsequently plating additional layers of metal over the termination stripes such that a part is solderable to a

substrate. An example of an electronic component with external electrodes formed by fired terminations and metal films plated thereon is disclosed in U.S. Patent No. 5,021,921 (Sano et al.). The application of terminations  
5 is often hard to control and can become problematic with reduction in chip sizes. U.S. Patent Nos. 6,232,144 B1 (McLoughlin) and 6,214,685 B1 (Clinton et al.) concern methods for forming terminations on selected regions of an electronic device.

10 The ever-shrinking size of electronic components makes it quite difficult to print termination stripes in a predetermined area with required precision. Thick film termination stripes are typically applied with a machine that grabs a chip and applies selective terminations with  
15 specially designed wheels. U.S. Patent Nos. 5,944,897 (Braden), 5,863,331 (Braden et al.), 5,753,299 (Garcia et al.), and 5,226,382 (Braden) disclose mechanical features and steps related to the application of termination stripes to a chip structure. Reduced component size or an  
20 increased number of termination contacts for an electronic chip device may cause the resolution limits of typical termination machines to become maxed out.

Other problems that can arise when trying to apply selective terminations include shifting of the termination  
25 lands, mispositioning of terminations such that internal electrode tabs are exposed or missed entirely, and missing wrap-around termination portions. Yet further problems may be caused when too thin a coating of the paint-like termination material is applied or when one portion of  
30 termination coating smears into another causing shorted termination lands. Another problem of the thick film systems is that it is often difficult to form termination

portions on only selected sides of a device, such as on a vertical surface. These and other concerns surrounding the provision of electrical terminations for monolithic devices create a need to provide cheap and effective termination features for electronic chip components.

Yet another known option related to termination application involves aligning a plurality of individual substrate components to a shadow mask. Parts can be loaded into a particularly designed fixture, such as that disclosed in U.S. Patent No. 4,919,076 (Lutz et al.), and then sputtered through a mask element. This is typically a very expensive manufacturing process, and thus other effective yet more cost efficient termination provisions may be desirable.

U.S. Patent Nos. 5,880,011 (Zablotny et al.), 5,770,476 (Stone), 6,141,846 (Miki), and 3,258,898 (Garibotti), respectively deal with aspects of the formation of terminations for various electronic components.

Additional background references that address methodology for forming multilayer ceramic devices include U.S. Patent Nos. 4,811,164 (Ling et al.), 4,266,265 (Maher), 4,241,378 (Dorrian), and 3,988,498 (Maher).

While various aspects and alternative features are known in the field of electronic components and terminations therefor, no one design has emerged that generally addresses all of the issues as discussed herein. The disclosures of all the foregoing United States patents are hereby fully incorporated into this application by reference thereto.

**BRIEF SUMMARY OF THE INVENTION**

The present subject matter recognizes and addresses various of the foregoing issues, and others concerning certain aspects of electrical terminations and related technology. Thus, broadly speaking, a principal object of some embodiments of the presently disclosed technology is improved termination features for electronic components. More particularly, the disclosed termination features are plated only and designed to eliminate or greatly simplify thick-film stripes that are typically printed along portions of a monolithic device for termination purposes.

Another principal object of some embodiments of the present subject matter is to provide a generally spiral-shaped inductor component for integration with a multilayer electronic component. More particularly, a plurality of internal conductive tab portions can be arranged on various device layers and exposed in a spiral pattern. The exposed pattern may then be subjected to a plating solution or other disclosed technologies may be used to form a plated inductive element.

Another principal object of the presently disclosed technology is to offer a way to guide the formation of plated material through the provision of internal electrode tabs and the optional placement of additional anchor tabs. Both internal electrode tabs and additional anchor tabs can facilitate the formation of secure and reliable external plating. Anchor tabs, which typically provide no internal electrical connections, may be provided for enhanced external termination connectivity, better mechanical integrity and deposition of plating materials.

Yet another principal object of some embodiments of the present subject matter is to provide termination

features for electronic components whereby typical thick-film termination stripes are eliminated or simplified, and only plated terminations are needed to effect an external electrode connection. Plated materials in accordance with the disclosed technology may comprise metallic conductors, resistive materials, and/or semi-conductive materials.

Another principal object of some embodiments of the present subject matter is to provide termination features for electronic components whereby ball limiting metallurgy (BLM) is created directly without the need to first provide termination stripes. Such ball-limiting metallurgy can be plated in accordance with the present technology in a variety of predetermined shapes and sizes.

A resultant advantage of some embodiments of the disclosed subject matter is that termination features for electronic components can be effected without the need for application by termination machinery, thus providing an ability to yield external terminations with resolution levels that may otherwise be unattainable. Such improved termination resolution also enables the provision of more terminations within a given component area and terminations with a much finer pitch.

Another object of some embodiments of the present technology is to provide termination features that enable an effective solder base with reduced susceptibility to solder leaching. Configuration of exposed electrode portions and anchor tab portions is designed such that selected adjacent exposed tab portions are decorated with plated termination material without undesired bridging among distinct termination locations. In fact, by altering the plating parameters by methods known in the art, one can tailor the degree of creep or spreading of the plating to

bridge gaps between exposed electrode portions or to leave them separated.

Yet another object of the present subject matter is that the disclosed technology can be utilized in accordance with a myriad of different termination configurations, including varied numbers and placement of external terminations. Plated terminations can be formed in accordance with a variety of different plating techniques as disclosed herein at locations that are self-determined by the provision of exposed conductive elements on the periphery of an electronic component.

A still further object of the subject plated component formation technology is to facilitate the production of cheaper and more effective electronic components in an expedient and reliable manner.

Additional objects and advantages of the present subject matter are set forth in, or will be apparent to those of ordinary skill in the art from, the detailed description herein. Also, it should be further appreciated by those of ordinary skill in the art that modifications and variations to the specifically illustrated, referenced, and discussed features and/or steps hereof may be practiced in various embodiments and uses of the disclosed technology without departing from the spirit and scope thereof, by virtue of present reference thereto. Such variations may include, but are not limited to, substitution of equivalent means, steps, features, or materials for those shown, referenced, or discussed, and the functional, operational, or positional reversal of various parts, features, steps, or the like.

Still further, it is to be understood that different embodiments, as well as different presently preferred

embodiments, of this technology may include various combinations or configurations of presently disclosed steps, features or elements, or their equivalents (including combinations of features or configurations thereof not expressly shown in the figures or stated in the detailed description).

Broad aspects of the present subject matter relate to plated terminations for a multilayer electronic component. Such a multilayer electronic component may preferably include a plurality of insulating substrates with a plurality of electrodes interleaved among the plurality of substrates. Selected of the plurality of electrodes preferably have a plurality of tab portions extending from selected portions and exposed along selected sides of the plurality of substrates. Selected of the exposed electrode tab portions are preferably stacked within predetermined distances of one another such that at least one layer of plated termination material may be formed along the periphery of the electronic component.

Additional general aspects of the present technology relate to anchor tabs for use with such aforementioned plated terminations. Anchor tabs may be additionally interleaved within the plurality of substrates of a multilayer electronic component and exposed at predetermined locations such that the formation of plated terminations is guided by the location of the exposed internal electrode tab portions and the exposed anchor tabs. With the provision of a sufficient number of exposed tabs, the formation of a plated termination is possible. Further, the anchor tabs provide greater mechanical strength to the final termination.



A first embodiment of the present technology concerns a multilayer electronic component having internal electrodes wherein selected of the internal electrode layers have tabs of varied width associated with the electrode layers. Such first embodiment of the present technology may include internal electrical vias to connect the various electrode layers. The first embodiment of the present technology may also include anchor tabs, in accordance with general aspects of the disclosed technology, wherein the anchor tabs may also be characterized by varied width. The varied tab widths may facilitate the formation of generally discoidal plated layer portions along the periphery of the multilayer electronic component.

A second embodiment of the present technology concerns a multilayer electronic component similar to the first embodiment and also including additional tabs associated with the electrode layers. The additional tabs extend in a direction opposite to selected of the electrode tabs mentioned with respect to the first embodiment and may be exposed at a selected surface of the multilayer electronic component. The additional tabs preferably are plated, or otherwise joined by standard thick film techniques, at the selected external surface and act as connection points for the internal electrodes, test terminals for the multilayer electronic component, and as expedients for the possible later electrochemical plating process.

A third embodiment of the present technology concerns a multilayer electronic component similar to the first embodiment and featuring additional electrode tabs that extend from selected electrode layers to multiple selected sides of the multilayer electronic component. As with the

second embodiment, these additional tabs may be plated externally on the multilayer electronic component and act as connection points for the internal electrodes as well as test terminals for the multilayer electronic component.

5        Yet another aspect of the present subject matter that may be incorporated with selected of the aforementioned exemplary embodiments of the present subject matter and others involves alternative features for forming a portion of plated material in a desired shape. An internal  
10 electrode configuration permits shaping the resulting termination by shifting a shaped pattern progressively toward the cut surface which forms the termination edge. For example, if the end of a tab is shaped as a semi-circle, then by exposing cross-sections of that shape and  
15 moving that shape each time by the thickness of the layer toward the surface to be cut, stopping at the center of the circle, the resultant pattern will trace out a semi-circle. If the shape is a triangle, the resultant termination will be a triangle, and so forth.

20        A still further aspect of the present subject matter that may be incorporated with select embodiments involves the formation of an internal inductor component. By printing a plurality of tabs that intersect the outer diameter of a via (to be drilled at a later time), and  
25 respectively rotating the position of each subsequently layered tab around the circumference of the via, a series of tabs will be exposed which form the path of a spiral. Subsequent plating will bridge those tabs, and form an actual spiral, which provides an inductor, a useful passive  
30 component addition.

Additional embodiments of the present subject matter, not necessarily expressed in this summarized section, may

include and incorporate various combinations of aspects of features or parts referenced in the summarized objectives above, and/or features or parts as otherwise discussed in this application.

5       The present subject matter equally concerns various exemplary corresponding methodologies for practice and manufacture of all of the herein referenced multilayer electronic component configurations and related plated termination technology.

10       Those of ordinary skill in the art will better appreciate the features and aspects of such embodiments, and others, upon review of the remainder of the specification.

15       **BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING**

A full and enabling description of the present subject matter, including the best mode thereof, directed to one of ordinary skill in the art, is set forth in the specification, which makes reference to the appended  
20 figures, in which:

Fig. 1 illustrates a side cross-sectional view of an exemplary multilayer interdigitated capacitor according to a known arrangement;

25 Fig. 2 illustrates an exploded plan view of a plurality of exemplary electrode layers for use in the multilayer interdigitated capacitor corresponding to the arrangement of Fig. 1;

Fig. 3 illustrates a front plan view of an exemplary multilayer interdigitated capacitor with a known electrode  
30 layer configuration such as in Figs. 1 and 2, further having tab portions exposed in accordance with broader

aspects of the present subject matter for application of the presently disclosed plated terminations;

Fig. 4 illustrates a front plan view of an exemplary multilayer interdigitated capacitor such as represented in Fig. 3 with plated terminations in accordance with the present subject matter;

Fig. 5 illustrates a side cross-sectional view of an exemplary multilayer interdigitated capacitor according to a first embodiment of the present subject matter;

Fig. 6 illustrates an exploded plan view of a plurality of exemplary electrode layers for use in the multilayer interdigitated capacitor embodiment of Fig. 5 in accordance with the present subject matter;

Fig. 7 illustrates a front plan view of an exemplary electrode layer configuration for a multilayer interdigitated capacitor corresponding to the embodiment of Figs. 5 and 6 in accordance with the present subject matter;

Fig. 8 illustrates a front plan view of an exemplary electrode layer configuration for a multilayer interdigitated capacitor corresponding to the embodiment of Figs. 5, 6, and 7 with the application of plating layers in accordance with the present subject matter;

Fig. 9 illustrates a side cross-sectional view of an exemplary multilayer interdigitated capacitor according to a second embodiment of the present subject matter;

Fig. 10 illustrates an exploded plan view of a plurality of exemplary electrode layers for use in the multilayer interdigitated capacitor embodiment of Fig. 9 in accordance with the present subject matter;

Fig. 11 illustrates a rear perspective view of an exemplary multilayer interdigitated capacitor with an

electrode layer configuration such as in Figs. 9 and 10 in accordance with the present subject matter;

Fig. 12 illustrates a side view of an exemplary multilayer interdigitated capacitor according to a third  
5 embodiment of the present subject matter;

Fig. 13 illustrates an exploded plan view of a plurality of exemplary electrode layers for use with the multilayer interdigitated capacitor of Fig. 12 in accordance with the present subject matter;

10 Fig. 14 illustrates a generally front perspective view of a multilayer interdigitated capacitor with an electrode layer configuration such as in Figs. 12 and 13 in accordance with the present subject matter;

Fig. 15 illustrates an exploded plan view of an  
15 alternative electrode layer and tab configuration for use with multilayer interdigitated capacitor embodiments in accordance with the present subject matter, whereby a desired exposed termination shape is effected by the progressive cross-sectioning of the desired shape as  
20 described by the exiting tabs;

Fig. 16 shows a detailed plan view of an exemplary slicing progression for electrode tabs such as depicted in the electrode layers of Fig. 15, which yield exiting tab portions for forming a generally circular shaped plated  
25 layer;

Fig. 17 shows a detailed front plan view of the resultant multilayer electrode tab configuration in accordance with the exemplary slicing progression depicted in Fig. 16, with layered electrode layers positioned to  
30 form a generally circular exposed pattern;

Fig. 18 illustrates a generally front perspective view of a multilayer interdigitated capacitor with an electrode

layer configuration and progressively sliced electrode tabs as depicted with regard to Figs. 15-17, respectively, in accordance with the present subject matter;

Fig. 19 illustrates an exploded plan view of a multi-layered tab configuration for use in embodiments of the present subject matter, whereby successive layers are designed to be superimposed on each other in the order shown, yielding respective concentrically positioned tabs around a common via location;

Fig. 20 illustrates a modified plan view of the exemplary layers of Fig. 20 stacked in succession around the same common via location, wherein the perspective is warped to show how the exposed sectioned tabs may look if one peers down through the common via location; and

Fig. 21 depicts a modified plan view, similar in perspective to Fig. 20, wherein a continuous spiral path is formed among the exposed sectioned tabs in accordance with the subject plating technology to create an inductive current path.

Repeat use of reference characters throughout the present specification and appended drawings is intended to represent same or analogous features or elements of the invention.

#### **DETAILED DESCRIPTION OF THE EMBODIMENTS**

As previously referenced, the present subject matter generally concerns improved component formation for multilayer electronic components. More particularly, the present subject matter relates to the utilization of plating technology in termination and inductive component formation as well for interconnection techniques for devices such as multilayer capacitors or integrated passive

components. The subject technology utilizes selective arrangements of exposed electrode tabs to facilitate the formation of plated electrical connections. The present subject matter concerns both the apparatuses embodied by  
5 such multilayer components as well as corresponding methodology for forming such components and the plated features therefor.

The subject component formation technology utilizes exposed electrode portions of structures such as monolithic  
10 capacitor arrays, multilayer capacitors including those with interdigitated electrode configurations, integrated passive components, and other electronic chip structures. Additional anchor tabs may be embedded within such monolithic components to provide stacked pluralities of  
15 exposed internal conductive portions to which plated terminations or interconnections may be formed and securely positioned along external surfaces of a device.

The subject plating technology and exposed tab features may be utilized in accordance with a plurality of  
20 different monolithic components. Figs. 3 and 4 combine known aspects of multilayer capacitor designs (such as depicted in Figs. 1 and 2) with the subject plated termination technology to depict broader aspects of the present subject matter. Figs. 5 through 8 respectively  
25 represent a first exemplary embodiment of the present technology featuring aspects of an interdigitated electrode layer configuration wherein electrode tabs of varied width generally extend to and are exposed on a selected side of a multilayer component. These and other aspects of plated  
30 terminations in accordance with the present subject matter are thereafter presented with respect to Figs. 9 through 11, which concern a second exemplary multilayer capacitor

embodiment with exposed conductive portions on two selected sides of the capacitor. Figs. 12 through 14 respectively illustrate aspects of a third exemplary embodiment of the disclosed technology with an electrode layer configuration having electrode tabs for exposure on multiple selected sides of a device. Figs. 15 through 18 describe alternative features for forming the exposed terminations with varied width as variously depicted in Figs. 5-14, respectively. Figs. 19 through 21 depict the formation of an inductive spiral by unique geometrical means in combination with the subject plated termination technology.

It should be noted that each of the exemplary embodiments as presented herein should not insinuate limitations of the disclosed technology. Features illustrated or described as part of one embodiment can be used in combination with another embodiment to yield further embodiments. Additionally, certain features may be interchanged with similar devices or features not mentioned yet which perform the same, similar or equivalent function.

Referring now to the drawings, Fig. 2 illustrates a known exemplary configuration of electrode layers 10 and 12 with respective electrode tabs 14 and 16 for use in a multilayer interdigitated capacitor or capacitor array. Electrode layers are generally arranged in a stacked multilayer arrangement within a body of dielectric material 18 (such as in Fig. 1) with tabs 14 and 16 extending from the layers such that electrode tabs extending from alternating electrode layers 10 and 12 are aligned in respective columns. The exemplary illustration of Fig. 2 depicts twenty such electrode layers with corresponding tabs 14 and 16, but arrangements as utilized with the present technology may in some instances contain more or



less electrode layers and numbers of respective tabs. This feature provides the option of creating capacitive elements with a large range of capacitance values (by choosing a relatively large number of electrodes).

5       The exemplary electrode layer configuration of Fig. 2 is not representative of a finished capacitor embodiment. Instead, Fig. 2 provides a reference for an intermediate aspect of exemplary capacitor and capacitor array configurations. The electrode layer configuration of Fig.  
10   2 can be utilized in accordance with an exemplary multilayer interdigitated capacitor such as displayed in Fig. 1.

      An interdigitated capacitor typically consists of a plurality of electrode layers, such as those shown in Fig.  
15   2 disposed in a body of dielectric material 18, such as seen in the exemplary interdigitated capacitor (IDC) configuration 20 of Fig. 1. Electrode layers 10 and 12 are disposed in the dielectric material 18 such that electrode tabs 14 and 16 extend to and are exposed at a selected side  
20   of IDC embodiment 20. Exemplary materials for such electrode layers may include platinum, nickel, a palladium-silver alloy, or other suitable conductive substances. Dielectric material 18 may comprise barium titanate, zinc oxide, alumina with low-fire glass, or other suitable  
25   ceramic or glass-bonded materials. Alternatively, the dielectric may be an organic compound such as an epoxy (with or without ceramic mixed in, with or without fiberglass), popular as circuit board materials, or other plastics common as dielectrics. In these cases the  
30   conductor is usually a copper foil which is chemically etched to provide the patterns.

A multilayer IDC component 20 such as that of Fig. 1 that incorporates the known exemplary electrode layer configuration of Fig. 2 is characterized by electrode portions 14 and 16 that are exposed on a selected side of IDC component 20. Other exemplary internal electrode configurations may be employed in a multilayer component such that internal electrode portions are exposed at different locations and/or on different numbers of sides of the device.

For example, consider the exemplary internal electrode layer configuration illustrated in the exploded view of Fig. 2. Alternating electrode layers 10 and 12 are provided with uniform width electrode tab portions 14 and 16 extending toward a single selected direction. Electrode tabs 14 and 16 for each set of alternating electrode layers are preferably arranged in a stacked configuration such that, for instance, tabs 14 from electrode layers 10 are aligned in respective columns and tabs 16 from electrode layers 12 are aligned in respective columns, wherein such tabs preferably extend to and are exposed on a single selected side of IDC 24.

Referring again to Fig. 1, a typical conventional termination for IDC embodiment 20 and for other monolithic electronic components comprises a printed and fired thick-film stripe 22 of silver, copper, or other suitable metal in a glass matrix, on top of which is plated a layer of nickel to promote leach resistance, and is followed by a layer of tin or solder alloy which protects the nickel from oxidation, and promotes an easily soldered termination.

A thick-film stripe 22 in accordance with such type of termination also typically requires printed application by a termination machine and printing wheel or other suitable component to transfer a metal-loaded paste. Such printing hardware may have resolution limits that make it hard to apply thick-film stripes, especially to smaller chips. A typical existing size for an IDC 20 or other electronic

component is about one hundred and twenty mils (thousandths of an inch) by sixty mils along the two opposing sets of sides with a thickness from top to bottom layers of about thirty mils. When more than four terminations need to be applied to a part this size or terminations are desired for a part with smaller dimensions, the resolution levels of specialized termination machinery often becomes a limitation in applying effective termination stripes.

The preceding describes the so-called thick-film preparation technique for the termination stripe 22. A more common method involves "thin-film" processing, which we describe below. According to one known technology, a first step in this preparation is achieved by first polishing the contact surface of the component 20. Thereafter, the monolithic component is mounted in a special fixture, usually along with many others, and a "shadow mask" is placed in precise registry above them. Chrome or similar non-solder-wettable metal or alloy is evaporated or sputtered through the mask to effect a termination stripe or island 22, analogous to the thick film version. Following the application of the termination stripe 22, either by thick or thin film techniques, the monolithic component is remasked and placed in another evaporation fixture where a layer of chrome, copper and gold alloy (Cr-Cu-Au) is evaporated onto the previously created chrome islands. This evaporation step is followed by yet another evaporation step, this time of a tin/lead (Sn/Pb) alloy. Alternative methods are known for this step, such as electroplating the alloy, or physically placing a solder-ball preform onto the BLM contact 30. Following this final evaporation, the monolithic component is placed in a hydrogen or other reducing atmosphere at elevated temperatures so as to reflow the tin/lead layer to

allow formation of the desired solder balls 40. Monolithic components made according to this process are then inspected and tested. Unfortunately the testing process distorts the soft solder balls 40 so that the components that test "good" must be further processed to reflow the tin/lead alloy to reform the solder balls. As can be appreciated, this process is not only time consuming but quite expensive to perform.

The present subject matter offers a termination arrangement that eliminates or greatly simplifies the provision of such typical thick-film termination stripes. By eliminating the less-controlled thick film stripe, the need for typical termination printing hardware is obviated. Termination features in accordance with the known technology focus more on the plated layer of nickel, tin, copper, etc. that is typically formed over a thick-film termination stripe.

Consider the exemplary capacitor array configuration 24 presented in Fig. 3. Capacitor array 24 is characterized by a plurality of internal electrodes and corresponding electrode tabs 14' and 16' (exposed portions of which are represented by the solid lines in Fig. 3) which are similar to the electrode tabs 14 and 16 of Figs. 1 and 2 and which are embedded in a body of dielectric material 18'. By subjecting capacitor array 24 or other electronic component with similarly exposed electrode tabs to an electroless plating solution, for example nickel or copper ionic solution, the formation of plated terminations 26 in accordance with the present subject matter, such as is shown in Fig. 4, is preferably effected. Exposure to such solution enables the exposed electrode tabs 14' and 16' to become deposited with nickel, copper, tin or other metallic plating. The resulting deposition of plated

material is preferably enough to effect an electrical connection between adjacent electrode tabs 14' and 16' in a stacked column.

In some exemplary embodiments of the disclosed technology, the distance between adjacent electrode tabs in a column of tabs should be no greater than about ten microns to ensure proper and continuous plating. The distance between adjacent columnar stacks of electrode tabs should thus be greater by at least a factor of 2 than this minimum distance to ensure that distinct terminations 26 do not run together. In some embodiments of the present technology, the distance between adjacent columnar stacks of exposed metallization is about four times the distance between adjacent exposed electrode tabs in a particular stack. By controlling the distance between exposed internal conductor portions, termination connectivity can be manipulated to form bridged or non-bridged terminations depending on the desired termination configuration.

Plated terminations 26 are thus guided by the positioning of the exposed electrode tabs 14' and 16'. This phenomena is hereafter referred to as "self-determining" since the formation of plated terminations 26 is determined by the configuration of exposed metallization at selected peripheral locations on a multilayer component, or capacitor array, 24. The exposed internal electrode tabs 14' and 16' also help to mechanically adhere terminations 26 to the periphery of capacitor array 24. Further assurance of complete plating coverage and bonding of the metals may be achieved by including resistance-reducing additives in the plating solution. A still further mechanism for enhancing the adhesion of metallic deposit that forms the subject plated terminations is to

thereafter heat the component in accordance with such technologies as baking, laser subjection, UV exposure, microwave exposure, arcwelding, etc.

The plated terminations 26 of Fig. 4 may be  
5 sufficiently formed for some component applications, but sometimes the exposed metallization from internal electrode tabs is insufficient to form the self-determining terminations of the present technology. In such case, it may be beneficial, and in some cases necessary, to provide  
10 additional anchor tabs embedded within select portions of a multilayer capacitor. Anchor tabs are short conductive tabs that typically offer no electrical functionality or internal connectivity to a component, but mechanically nucleate and secure additional plated termination along the  
15 periphery of a monolithic device. Exposed anchor tabs in combination with exposed internal electrode portions can provide sufficient exposed metallization to create more effective and more evenly shaped self-determining terminations.

20 There are several different techniques that can potentially be used to form plated terminations, such as terminations 26 on multilayer capacitor embodiment 24 of Fig. 4. As previously addressed, a first method corresponds to electroplating or electrochemical  
25 deposition, wherein an electronic component with exposed conductive portions is exposed to a plating solution such as electrolytic nickel or electrolytic tin characterized by an electrical bias. The component itself is then biased to a polarity opposite that of the plating solution, and  
30 conductive elements in the plating solution are attracted to the exposed metallization of the component. Such a plating technique with no polar biasing is referred to as

electrolytic plating, and can be employed in conjunction with electroless plating solutions such as nickel or copper ionic solution.

5 In accordance with electrochemical deposition and electroless plating techniques, a component such as IDC 24 of Fig. 4, is preferably submersed in an appropriate plating solution for a particular amount of time. With certain embodiments of the present subject matter, no longer than fifteen minutes is required for enough plating  
10 material to deposit at exposed conductive locations along a component such that buildup is enough to spread the plating material in a perpendicular direction to the exposed conductive locations and create a connection among selected adjacent exposed conductive portions.

15 Another technique that may be utilized in accordance with the formation of the subject plated terminations involves magnetic attraction of plating material. For instance, nickel particles suspended in a bath solution can be attracted to similarly conductive exposed electrode tabs  
20 and anchor tabs of a multilayer component by taking advantage of the magnetic properties of nickel. Other materials with similar magnetic properties may be employed in the formation of plated terminations.

A still further technique regarding the application of  
25 plated termination material to exposed electrode tabs and anchor tabs of a multilayer component involves the principles of electrophoretics or electrostatics. In accordance with such exemplary technology, a bath solution contains electrostatically charged particles. An IDC or  
30 other multilayer component with exposed conductive portions may then be biased with an opposite charge and subjected to the bath solution such that the charged particles are

deposited at select locations on the component. This technique is particularly useful in the application of glass and other semiconductive or nonconductive materials. Once such materials are deposited, it is possible to  
5 thereafter convert the deposited materials to conductive materials by intermediate application of sufficient heat to the component.

One particular methodology for forming plated terminations in accordance with the present technology  
10 relates to a combination of the above-referenced plating application techniques. A multilayer component may first be submersed in an electroless plating solution, such as copper ionic solution, to deposit an initial layer of copper over exposed tab portions, and provide a larger  
15 contact area. The plating technique may then be switched to an electrochemical plating system which allows for a faster buildup of copper on the selected portions of such component.

In accordance with the different available techniques  
20 for plating material to exposed metallization of a multilayer component in accordance with the present technology, different types of materials may be used to create the plated terminations and form electrical connections to internal features of an electrical  
25 component. For instance, metallic conductors such as nickel, copper, tin, etc. may be utilized as well as suitable resistive conductors or semi-conductive materials, and/or combinations of selected of these different types of materials.

30 A still further plating alternative corresponds to forming a layer of metallic plating, and then electroplating a resistive alloy over such metallic



plating. Plating layers can be provided alone or in combination to provide a variety of different plated termination configurations. A fundamental of such plated terminations is that the self-determining plating is configured by the design and positioning of exposed conductive portions along the periphery of a component.

Such particular orientation of internal electrode portions and anchor tabs may be provided in a variety of different configurations to facilitate the formation of plated terminations in accordance with the present subject matter. More particular exemplary embodiments of the present technology are hereafter presented to provide more detailed representation of exemplary of such configurations.

With specific reference to Figs. 5-8 respectively, a first embodiment of the present subject matter is illustrated. Differences between the known technology and such first embodiment of the present technology can most easily be seen by comparing Figs. 5-6 with Figs. 1-2 respectively. More particularly, the first exemplary embodiment of the present technology 100 as depicted in Fig. 5 is distinguished by its absence of an equivalent to the thick or thin film terminations 22 illustrated in Fig. 1. The present technology allows for the omission of the termination stripe 22 due, in part, to the morphing configurations of the electrode tabs 114 and 116.

With reference to Figs. 5, 6 and 7, electrodes 110 and 112 of monolithic interdigitated capacitor (IDC) 100 are stacked in an alternating series and are configured with tabs 114 and 116 extending toward a selected side of the capacitor. Tabs 114 and 116 vary in both length and width. As can more clearly be seen from Figs. 5 and 6, the tabs

114 and 116 from selected uppermost and lowermost layers 110 and 112 are somewhat shorter than the tabs from more central layers and, as such, are not exposed at a surface of the insulating material 128 as are the more central tabs. Additionally, as can be more clearly seen from Figs. 6 and 7, tabs 114 and 116 are made to vary in width so that the exposed end surfaces of the tabs on the central most electrode layers form respective circular patterns as most clearly seen in Fig. 7.

With continued reference to Figs. 6 and 7, additional tabs 118 and 120 are illustrated. These tabs are anchor tabs similar to those previously mentioned in that they are typically electrically isolated from the active electrode tabs 114 and 116 and contribute substantially no electrical function to the IDC. These anchor tabs may vary in width in a manner similar to the active electrode tabs and function with the active electrode tabs as anchor points for the plating layer portions 130 (of Fig. 8) and as additional nucleation points for the plating layer portions during the actual plating process. Exposed anchor tabs in combination with exposed active electrode portions can provide sufficient exposed metallization to create more effective self-determining plating layers 130. As a result of the operation of the self-determining circular plating resulting from the varying widths of the active and anchor tabs, ball limiting metallurgy is directly provided in a significantly easier and cheaper manner.

Referring again to Figs. 5 and 7, as previously noted, a portion of the electrode tabs 114 and 116 attached to electrodes 110 and 112 are shorter than others of the electrode tabs. These shorter tabs do not reach the surface of the IDC 100 as illustrated by the dotted lines

122 and 124 of Fig. 7. In order to electrically connect the electrodes associated with these shorter tabs to the other electrodes of the IDC 100, at least one internal via 146 is provided. The IDC 100 may be completed by providing  
5 a solder ball 140 on selected portions of BLM 130. It should be appreciated that while only one internal via 146 and one solder ball 140 is depicted in the illustration of Fig. 5, a plurality of such vias (for instance, one per  
arranged column of electrode tabs 114 or 116) and solder  
10 balls may preferably be utilized with the subject IDC 100.

Solder balls 140 as applied to the plated BLM portions 130 may render a part compatible with BGA mounting technology for connecting the completed IDC to other components including printed wiring boards or other  
15 substrate environments. Solder balls 140 may be formed by first evaporating a lead alloy onto the plating layer 130, which acts as a ball limiting metallurgy. Alternative methods for accomplishing this have been described above, which include electroplating the solder alloy onto the BLM  
20 contact, or physically placing a solder perform onto it. After the lead alloy is evaporated onto the plating layer, the IDC is heated in a Hydrogen, reducing, or neutral atmosphere to allow the lead alloy to reflow without oxidation. The reflowing of the lead alloy solder, because  
25 of the surface tension of the molten material, forms the solder into a ball configuration.

Referring now to Figs. 9 through 11, a second embodiment of the present subject matter will be described. With reference to Figs. 9 and 10, the principle differences  
30 between this alternative arrangement of the present subject matter and the first embodiment of Figs. 5 through 8 can be seen. In particular, this second embodiment provides

electrode tabs extending toward two opposing sides of the IDC 200. As illustrated in Figs. 9 and 10, electrode tabs 214 and 216 are substantially similar to electrode tabs 114 and 116 of the IDC embodiment 100 illustrated in Figs. 5 through 8. Moreover, anchor tabs 218 and 220 are substantially similar to anchor tabs 118 and 120 of the IDC embodiment 100 illustrated in Figs. 5 through 8. Particular to this embodiment, however, are electrode tabs 219 and 221 that extend in a direction opposite to electrode tabs 218 and 220 and are of a sufficient length to reach the rear surface of the IDC as illustrated in Fig. 11. For convenience, the surface of the IDC on which the solder balls 240 are attached is denoted the "front" surface while the side opposite to the front side surface is denoted the "rear" surface. Such particular reference to orientation is used merely for the sake of convenience and should in no way convey limitations of the present technology.

Respective columns of electrode tabs 219 and 221 are provided to yield at least one plurality of exposed portions of a given polarity and at least one plurality of exposed portions of the opposing polarity. Each respective column of exposed portions of tabs 219 and 221 may be electrically connected together with shorting layers 250 as represented in Fig. 9. Such shorting layers can be fabricated by the electroless plating process as described herein, or they may be striped on using conventional thick film techniques. In any case, these layers 250 are typically columns similar to the plating layers 26 illustrated in Fig. 4 and perform a function similar to that of the internal vias 146 of the first embodiment of the present technology. Although not illustrated, it should be appreciated that anchor tabs as utilized with

plated layers of the present technology may also be employed in the formation of layers 250. The second embodiment of the present technology is also characterized by ball limiting metallurgy 230 and solder balls 240, similar to corresponding elements 130 and 140 of the first embodiment shown in Figs. 5 through 8 respectively.

Turning now to Figs. 12 through 14, a third embodiment of the present technology is illustrated. The embodiment of Figs. 12 through 14 features many selected elements of the previous embodiments but differs principally in the formation and direction of electrode tabs and anchor tabs, including the location of exposed portions thereof on the periphery of IDC 300. In the second more particular embodiment, electrode tabs 219 and 221 extend to the rear surface of the IDC 200 and are interconnected there by way of plating layer portions 250. In the third present embodiment 300, the equivalently functioning electrode tabs 319 and 321, as best seen in Fig. 13, are generally respectively configured at right angles to the direction of the electrode tabs 314 and 316 and extend toward multiple selected sides of the IDC 300. The electrode tabs 319 and 321 are of such a length as to be exposed at opposing side surfaces of IDC 300. As seen in the isometric view of Fig. 14, tabs 321 are exposed on a first selected side, while tabs 319 reach the surface of the opposing side of IDC 300 (not shown). In a manner similar to that of the previous embodiment, these electrode tabs 319 and 321 are electrically connected together respectively by way of separate plating layers 350 located on opposing sides of IDC 300. One such plating layer 350 is depicted in the side view of Fig. 12. Although not illustrated, it should be appreciated that anchor tabs as utilized with plated

layers of the present technology may also be employed in the formation of layers 350. The front surface of the IDC embodiment 300 also features plating layers 330 and solder balls 340, similar to the corresponding elements of the other more particular IDC embodiments.

Each of the aforementioned embodiments discussed with respect to Figs. 5-14 incorporate electrode tabs with varied width in order to form an exposed tab pattern of a desired shape (e.g., a discoidal pattern). When forming such multilayer devices, it should be appreciated by one of ordinary skill in the art that it is desirable to keep tight registration or alignment of each of the internal layers. If the internal electrodes are formed with the wrong width or misaligned at too great a distance in either direction, the intended locations of exposed tabs and corresponding portions of material plated thereto can be affected. In some cases, parametric variation of the various mechanical and electrical characteristics of the device can be affected. In extreme cases, misaligned electrodes can result in undesired shorting between adjacent terminations.

In accordance with potential concerns of some embodiments of plated termination formation, aspects of an alternative exemplary electrode layer and corresponding tab configuration for use in accordance with the present subject matter is represented in Figs. 15 through 18, respectively. It should be appreciated that such alternative formation can be selectively employed in combination with any of the aforementioned embodiments of the present subject matter to yield still further embodiments. An exploded plan view of multiple exemplary electrode layers for combining in a successively stacked

relationship within a body of dielectric material is depicted in Fig. 15 (with two-dimensional reference in the X and Y directions). Electrodes 410 alternate with electrodes 412 to provide a multilayer structure with a desired capacitance value, and the number of such electrodes 410 and 412 can vary accordingly to satisfy such desired criteria. Electrode tabs 414 extend from selected portions of respective electrodes 410 and electrode tabs 416 extend from selected portions of respective electrodes 412 and typically exit a capacitive structure to provide electrical connection to the respective electrodes. Each electrode tab 414 and 416 is preferably initially provided with the same shape, each having a generally semicircular end portion. Respective anchor tabs 418 and 420 are also provided with selected electrode layers with a shape that matches with the ends of the electrode tabs. Provision of the electrode layer and tab configuration of Fig. 15 is simpler in some aspects than the configurations of 6, 10 and 13 since all electrode tabs and anchor tabs are formed with the same general shape.

Referring still to Fig. 15, the electrode layer and corresponding tab configurations are positioned with reference to alignment in both the "X" and "Y" directions. The layers may then be successively stacked in the "Z" direction (perpendicular to the drawing). However, if the ends of the tabs are shaped in a semi-circle, and allowed to shift slightly in the "X" direction, then the subsequent dicing, or cutting, will reveal different portions of that semi-circle, and the result will be exposed tabs with different respective widths. This is shown more specifically in Fig. 16, which illustrates a detailed view of an exemplary tab 416 and different exemplary cut

positions therefor. Although discussed with reference to tabs 416, it should be appreciated that similar cut positions are also applied to selected electrode tabs 414 and to anchor tabs 418 and 420.

5 Referring to Figs. 16 and 17, a first electrode position A yields no cutting or intersection of tab 416, so there will not be any portion of the tab visible on the outside of the device. This is also depicted in Fig. 17 which shows the resultant profile of all the tab cuts. At  
10 position A, there is no exposure. In Fig. 16, if the pattern is moved in an increment equal to the thickness of the substrate on which each electrode is placed, then the slightest amount of the tab will be cut at position B, and a short exposure will be seen as depicted in Fig. 17.  
15 Thus, as we progressively move the pattern in the "X" direction, each time incrementing by the substrate thickness, we will trace the shape of the semi-circle through position F. Then if we reverse the direction, we will create the other half of the circle with cuts at  
20 positions E, D, C and B, respectively. Cut A again will hide the tab ends inside. It is desirable to keep that position for many layers, in order to separate the circular patterns when multiple such patterns are desired.

Fig. 18 illustrates a generally front perspective view  
25 of the resultant multilayer device 400, utilizing the exemplary electrode layer configuration of Fig. 15 with the varied electrode positioning represented in Figs. 16 and 17. The intersected tabs from the progressive cuts, are seen as 414 for one polarity, and 416 for the other. Also  
30 visible in Fig. 18 are the anchor tabs which have been formed from the circular patterns 418 and 420. The resultant positioning of the exposed tab portions



facilitates the deposition of a generally circular portion of plated material thereon. It should be appreciated that other formations, such as triangular shaped plated portions, may also be formed in accordance with the present subject matter either by providing tabs with varied widths or by varying the position of a triangular shaped tab, similar to the technology presented with regard to Figs. 15-18.

In the exemplary embodiments of Figs. 15-18, the internal electrodes are provided with side tabs 419 and 421 to which additional side terminations can be plated to provide respective connections among the opposing internal electrodes. This is similar to the side tabs of Figs. 12-14, but are characterized by a slightly skewed alignment, as represented by portion 423 in Fig. 18, as the electrode patterns have been shifted in the "X" direction. Although the exemplary embodiment of Figs. 15-18 is depicted with connective side terminations, it should be appreciated that other connection configurations, such as the internal vias of Fig. 5 or the rear terminations of Fig. 9, may also be employed in accordance with this exemplary embodiment.

It should be appreciated that the multilayer interdigitated capacitor embodiments presented in Figs. 3 through 18, respectively, are presented merely as examples of the disclosed technology, including intermediate aspects thereof. In most of the examples, four or more general columns of electrodes are depicted, but a fewer or greater number of electrode columns are possible, depending on the desired component configuration. It is possible to form plated terminations along any selected portion of any selected component side in accordance with the disclosed technology. Such plated terminations may include a single

layer of plated conductive material, resistive material, or semi-conductive material, or a multilayer combination of selected of such materials.

The exemplary embodiments discussed above have  
5 utilized the subject plating technique to form termination features. The same technology can be used for other useful electronic purposes, as can be seen in the following example. Figs. 19 through 21 describe the construction of a spiral-shaped inductor that can be formed using the  
10 disclosed plating process. Fig. 19 shows an exploded plan view of exemplary layers which may be stacked and positioned in registry with respect to a virtual circle 562. Each layer consists of a portion of dielectric material 560, and may further include a tab 564a-564h  
15 (hereafter collectively referred to as 564) printed such that it intersects the virtual circle 562. At a later time, the virtual circle location will be drilled to form an actual cylindrical hole through the multilayer component.

20 The plurality of tabs in Fig. 19 are variously depicted at different positions around the virtual circle 562 relative to the direction indicated by reference arrow 555. A first layer (the bottommost layer illustrated in Fig. 19) includes a tab portion 564a' that is positioned  
25 generally in the same direction as reference arrow 555. A second layer includes a tab portion 564b that is positioned about forty-five degrees clockwise from reference direction 555. Each subsequent patterned layer rotates the tab feature 564 an additional forty-five  
30 degrees clockwise from the tab direction of the previous layer, eventually completing a full rotation, with a layer having another tab 564a positioned at reference direction

555. After such layers are stacked, they are laminated with a blank cover layer having no tab feature. A hole may then be drilled within the virtual circle to expose each tab portion within the generally cylindrical hole.

5 Fig. 20 provides a skewed perspective of such a multilayer configuration after the layers of Fig. 19 are successively stacked in order on the same virtual circle alignment. The perspective is warped for illustrative convenience to show how the sectioned tabs may look when  
10 peering downward through the drilled hole. Each tab 564 is exposed to trace a spiral downward from the top 580 of hole 562, to the bottom 582 of hole 562. The columnar hole usually has the same diameter all the way through the laminate. After the part is fired, the inside of the hole  
15 can be exposed to the electroless copper, as described previously, and the tabs will become joined in a continuous path, seen as 584 in Fig. 21. It should be appreciated that other plating solutions and techniques as disclosed herein may also be used to form the plated spiral 584.

20 With regard to the exemplary embodiment of Figs. 19-21, it should be recognized that although we show the tabs 564 as isolated strips, for the sake of drawing simplicity, provisions may typically be needed for electrically contacting the respective end tabs 564a for the purpose of  
25 connecting the resultant inductor to other parts of the circuit, and for temporarily connecting the other tabs 564b-564h for plating should the part be designed such that electroless copper will not bridge.

It should be further appreciated that a number of  
30 variations could be made to the exemplary configuration illustrated in Figs. 19-21. For example, we have shown eight tab segments joined to make a single turn spiral. A

single turn could be made with just two tab patterns, as well. Further, it is generally desired to have maximum inductance, which requires multiple turns. This can be easily accomplished with the disclosed technique by  
5 decreasing the number of tab segments per rotation, or increasing the number of layers, or both. As a practical matter, since the electroless plating technique has a resolution limit, four tab segments is about the minimum number when working with material that is about ten microns  
10 thick. That allows bridging to occur over the ten microns, but isolates itself for the forty micron separations between each adjacent spiral turns.

A related advantage of the disclosed plating technology relative to the formation of inductive  
15 components is that additional copper (or silver or other good conductor) can be plated over the spiral path to increase the "Q" factor, a measure of inductor performance. One could even place a magnetic plug into the hole 562, to increase the inductance even further.

20 While the present subject matter has been described in detail with respect to specific embodiments thereof, it will be appreciated that those skilled in the art, upon attaining an understanding of the foregoing may readily adapt the present technology for alterations to, variations  
25 of, and equivalents to such embodiments. Accordingly, the scope of the present disclosure is by way of example rather than by way of limitation, and the subject disclosure does not preclude inclusion of such modifications, variations, and/or additions to the present subject matter as would be  
30 readily apparent to one of ordinary skill in the art.

## CLAIMS

1. A multi-layer electronic component, comprising:  
a plurality of insulating substrates each having an upper and a  
5 lower surface, said plurality of insulating substrates being delimited  
laterally by edges;  
a plurality of electrodes interleaved between said plurality of  
insulating substrates, said plurality of electrodes having tab portions  
thereof with respectively varied widths exposed along at least one edge of  
10 said plurality of insulating substrates; and  
at least one layer of plated termination material connecting selected  
of said tab portions.
2. A multi-layer electronic component as claimed in claim 1, in which  
15 the at least one layer of plated termination material is formed in a  
generally discoidal configuration.
3. A multi-layer electronic component as claimed in claim 1 or claim  
2, further comprising:  
20 a plurality of electronically isolated anchor tabs interspersed among  
said plurality of insulating substrates, said anchor tabs having  
respectively varied width portions thereof exposed along at least one edge  
of said plurality of insulating substrates.
- 25 4. A multi-layer electronic component as claimed in claim 3, in which  
the at least one layer of plated termination material connects selected of  
said exposed tab portions of selected of said plurality of electrodes and  
selected of the exposed portions of said plurality of electrically isolated  
anchor tabs.
- 30 5. A multi-layer electronic component as claimed in claim 3 or claim

4, in which selected of said exposed tab portions of said selected electrodes and selected of said plurality of electrically isolated anchor tabs are aligned in a column at selected edges of said plurality of insulating substrates.

5

6. A multi-layer electronic component as claimed in any preceding claim, in which said at least one layer of plated termination material comprises a metallic conductive material and the exposed portions of the electrode tabs are configured to guide the formation of said at least one  
10 layer of plated termination material to directly provide ball limiting metallurgy.

7. A multi-layer electronic component as claimed in any of claims 3 to 6, in which the exposed tab portions of said electrodes and the exposed  
15 portion of said anchor tabs are spaced one from another such that said tabs act as nucleation and guide points for the at least one layer of plated termination material.

8. A multi-layer electronic component as claimed in any preceding  
20 claim, in which said at least one layer of plated termination material comprises a metallic conductive material, a resistive material, or a semiconductive material.

9. A multi-layer electronic component as claimed in any preceding  
25 claim, in which said at least one layer of plated termination material comprises a plurality of layers of electronically diverse material.

10. A multi-layer electronic component as claimed in claim 9, in which said plurality of layers of electrically diverse material comprise at least a  
30 layer of resistive material sandwiched between layers of conductive material.

11. A multi-layer electronic component, comprising:

a plurality of dielectric layers, each of said plurality of dielectric layers being delimited laterally by edges;

5 a plurality of electrode layers interleaved between said plurality of dielectric layers, selected ones of said plurality of electric layers having respectively varied width tab portions exposed at selected edges of said plurality of dielectric layers;

10 a plurality of electrically isolated anchor tabs with respectively varied widths interspersed among and exposed at selected edges of selected of said plurality of dielectric layers; and

at least one termination layer connecting exposed portions of selected of said plurality of electrically isolated anchor tabs and exposed tab portions of selected of said plurality of electrode layers.

15 12. A multi-layer electronic component as claimed in claim 11, further comprising a plurality of termination layers, wherein selected of said plurality of termination layers connect selected of said exposed varied width tab portions of selected of said plurality of electrodes and selected of said plurality of electrically isolated varied width anchor tabs.

20

13. A multi-layer electronic component as claimed in claim 12, in which selected of said exposed varied width tab portions of said selected of said electrode layers and selected of said plurality of electrically isolated varied width anchor tabs are aligned in columns at selected edges  
25 of said plurality of dielectric layers.

14. A multi-layer electronic component as claimed in any of claims 11 to 13, in which said at least one termination layer is formed in a generally discoidal configuration.

30

15. A multi-layer electronic component as claimed in any of claims 11 to 14, in which the exposed varied width tab portions and the exposed varied width anchor tabs are spaced one from another such that such tabs act as nucleation and guide points for the at least one termination layer.

5

16. A multi-layer electronic component as claimed in any of claims 11 to 15, in which said at least one termination layer comprises a metallic conductive material, a resistive material, or a semiconductive material.

10

17. A multi-layer electronic component as claimed in any of claims 11 to 15, in which said at least one termination layer comprises a metallic conductive material and the exposed portions of the electrode tabs are configured to guide the formation of the at least one termination layer to directly provide ball limiting metallurgy.

15

18. A multi-layer electronic component as claimed in any of claims 11 to 15, in which said at least one termination layer comprises a plurality of layers of electrically diverse material.

20

19. A multi-layer electronic component as claimed in claim 18, in which said plurality of layers of electrically diverse material comprise at least a layer of resistive material sandwiched between layers of conductive material.

25

20. A multi-layer electronic component, comprising:  
a plurality of dielectric layers;  
a plurality of electrically conductive tabs spirally aligned and interspersed among said plurality of dielectric layers; and  
a layer of termination material connecting said plurality of tabs.

30



21. A multi-layer electronic component as claimed in claim 20, in which said layer of termination material comprises a metallic conductive material.
- 5 22. A method of making a multi-layer electronic component, comprising the steps of:
- providing a plurality of dielectric layers;
  - providing a plurality of conductive tabs spirally aligned and interspersed among said plurality of dielectric layers; and
  - 10 plating a layer of termination material on said conductive tabs whereby said plurality of tabs are connected together.
23. A method as claimed in claim 22, in which the step of providing a plurality of conductive tabs comprises printing individual layers of
- 15 conductive material at selected locations on selected surfaces of selected dielectric layers.
24. A method as claimed in claim 22 or claim 23, further comprising the step of:
- 20 exposing portions of the plurality of conductive tabs by opening a via through the plurality of dielectric layers prior to the step of plating.
25. A method as claimed in any of claims 22 to 24, in which said step of plating comprises exposing said conductive tabs to an electroless
- 25 copper solution.
26. A method of directing the formation of plating material in a multi-layer electronic component, comprising the steps of:
- embedding a plurality of conductive tabs at selected locations in a
  - 30 plurality of layers of dielectric material; and

exposing the plurality of conductive tabs to a plating solution whereby the embedded conductive tabs form nucleation points for plating material within the plating solution and guide the direction of the deposition of the plating material along the exposed plurality of conductive tabs.

27. The method of claim 26, in which the surface area and positioning of the exposed conductive tabs is varied whereby the surface area and geometry of the plating material is controlled.

10

28. The method of claim 27, in which the surface area and positioning of the exposed conductive tabs is varied such that the surface area of the plating material is formed into a generally planar discoidal formation.

29. The method of claim 28, in which the generally discoidal formation of plating material is configured as ball limiting metallurgy.

30. The method of claim 27, in which the surface area and positioning of the exposed conductive tabs is varied such that the surface area of the plating material is formed into a generally linear spiral formation.

20

31. The method of claim 30, in which the generally linear spiral formation is configured as an inductive element.

32. A method of making a multi-layer electronic component, comprising the steps of:

25

providing a plurality of insulating substrates each having an upper and a lower surface, said substrates each being delimited laterally by edges;

interleaving a plurality of electrodes between selected of said plurality of insulating substrates;

30

exposing varied width portions of said electrodes along at least one edge of said plurality of substrates; and

plating at least one layer of termination material on the exposed portions of said electrodes.

5

33. The method of claim 32, further comprising the step of continuing the plating process until the exposed portions of said electrodes are connected.

10 34. The method of claim 32 or claim 33, in which the step of plating is performed using an electroless process followed by an electrochemical process.

15 35. The method of claim 32 or claim 33, in which the step of plating is performed using an electroless process.

36. The method of claim 35, in which the electroless process comprises submersing the multi-layer electronic component in an electroless copper plating solution to form a copper termination layer.

20

37. The method of claim 36, further comprising the step of covering the copper termination layer with a resistive layer.

25 38. The method of claim 37, further comprising the step of plating the resistive layer with a conductive layer.

39. The method of claim 32, in which the step of exposing comprises:  
providing the electrodes with non-uniformly cross-sectioned tab portions;

30 positioning the electrodes at laterally displaced locations among said dielectric layers; and

cleaving edges of the interleaved electrodes and dielectric layers whereby varied width portions of the tab portion of the electrodes are exposed.

5 40. The method of claim 39, in which said providing step comprises providing the electrodes with rounded tab portions.

41. A multi-layer electronic component comprising:

a plurality of stacked dielectric layers;

10 a plurality of conductive tabs positioned at selected locations on said plurality of stacked dielectric layers; and

at least one layer of termination material connecting selected of said plurality of conductive tabs.

15 42. A multi-layer electronic component as claimed in claim 41, in which said plurality of conductive tabs are positioned at selected edges of said plurality of dielectric layers.

20 43. A multi-layer electronic component as claimed in claim 41 or claim 42, in which said plurality of conductive tabs are aligned in columns.

44. A multi-layer electronic component as claimed in any of claims 41 to 43, in which the plurality of conductive tabs are varied in width to form a predetermined geometric pattern.

25

45. A multi-layer electronic component as claimed in claim 44, in which said predetermined geometric pattern is a pattern selected from the group consisting of, a generally discoidal configuration, a generally triangular configuration and a generally rectangular pattern.

30

46. A multi-layer electronic component as claimed in claim 44, wherein the geometric pattern is generally circular and the termination material connecting selected of the conductive tabs forms ball limiting metallurgy for the multi-layer component.

5

47. A multi-layer electronic component as claimed in any of claims 41 to 46, in which said plurality of conductive tabs are positioned at selected angular positions around a cylindrical via piercing a central location of said plurality of dielectric layers.

10

48. A multi-layer electronic component as claimed in claim 47, in which the termination material connecting selected of the conductive tabs is a metallic material and forms a spiral inductor within said cylindrical via.

15

49. A multi-layer electronic component as claimed in any of claims 41 to 48, in which said plurality of conductive tabs are positioned at selected central locations of said plurality of dielectric layers.

20 50. A multi-layer electronic component substantially as described herein with reference to and as illustrated in Figures 3 and 4 of the accompanying drawings.

25 51. A multi-layer electronic component substantially as described herein with reference to and as illustrated in Figures 5 to 8 of the accompanying drawings.

30 52. A multi-layer electronic component substantially as described herein with reference to and as illustrated in Figures 9 to 11 of the accompanying drawings.

53. A multi-layer electronic component substantially as described herein with reference to and as illustrated in Figures 12 to 14 of the accompanying drawings.

5 54. A multi-layer electronic component substantially as described herein with reference to and as illustrated in Figures 15 to 18 of the accompanying drawings.

10 55. A multi-layer electronic component substantially as described herein with reference to and as illustrated in Figures 19 to 21 of the accompanying drawings.

15 56. A method of making a multi-layer electronic component substantially as described herein with reference to and as illustrated in Figures 3 to 21 of the accompanying drawings.

20 57. A method of directing the formation of plating material in a multi-layer electronic component substantially as described herein with reference to and as illustrated in Figures 3 to 21 of the accompanying drawings.



INVESTOR IN PEOPLE

Application No: GB 0308656.8  
Claims searched: 1-19 & 32-40

47  
Examiner: Peter Mason  
Date of search: 10 October 2003

## Patents Act 1977 : Search Report under Section 17

### Documents considered to be relevant:

Category	Relevant to claims	Identity of document and passage or figure of particular relevance
A	-	US 5,880,925 (AVX CORPORATION) See whole document.
A,E	-	JP 2002 164257 A (TDK CORPORATION) See WPI and PAJ Abstract.
A	-	JP 06 168845 A (MARCON ELECTRONICS CO) See WPI and PAJ Abstract.

### Categories:

X	Document indicating lack of novelty or inventive step	A	Document indicating technological background and/or state of the art.
Y	Document indicating lack of inventive step if combined with one or more other documents of same category.	P	Document published on or after the declared priority date but before the filing date of this invention.
&	Member of the same patent family	E	Patent document published on or after, but with priority date earlier than, the filing date of this application

### Field of Search:

Search of GB, EP, WO & US patent documents classified in the following areas of the UKC<sup>v</sup>:

H1M:  
H1R:

Worldwide search of patent documents classified in the following areas of the IPC<sup>7</sup>:

H01G:  
H05K:

The following online and other databases have been used in the preparation of this search report:

EPODOC, JAPIO, WPI

**THIS PAGE BLANK (USPTO)**



**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)